



Espacenet

Bibliographic data: EP1184525 (A1) — 2002-03-06

Fibreboard

Inventor(s): BITZI JOHANN DIPL-ING [CH]; HASCH JOACHIM DIPL-HOLZWIRT [DE]; STADELMANN RENE DIPL-ING [CH]; SCHWIND VOLKER DIPL-HOLZWIRT [DE] \pm

Applicant(s): KRONOTEC AG [CH] \pm

Classification:
 - **international:** **E04C2/16**; (IPC1-7): E04C2/16
 - **European:** E04C2/16

Application number: EP20010119297 20010810


Priority number (s): DE20001042534 20000830

Also published as: EP1184525 (B1) PT1184525 (E) ES2231359 (T3)
DE10042534 (A1) AT281570 (T)

Abstract of EP1184525 (A1)

The fiberboard, using fibers with a lignocellulose content and a polyurethane glue as the bonding agent, has a mean bulk density of 350 kg/m³. The density curve in the core (1) is constant over a range of two-thirds of the board thickness (s), symmetrically to the center (M). The

deviation between the mean density at the core and the maximum density at the covering layer (2) is a maximum of 15% and, at the most, 30 kg/m³.



Last updated: 14.03.2012 Worldwide Database 5.7.39; 93p